

TIKKURILA ET777 2 PACK ETCH PRIMER AND TIKKURILA PLS SEMI GLOSS PU TOPCOAT ON EXISTING GARAGE DOORS AND PANELS.

Remove dirt, oil and grease etc, by washing down with TIKKURILA PROFESSIONAL CLEANING AGENT then rinse with clean water and allow to dry thoroughly.

Rub down all surfaces with 180 grade silicon carbide sanding pads prior to priming. Wipe all surfaces with 1031 thinners.

Apply 1 coat of Tikkurila ET777 primer by airless spray and allow to dry. Thin if necessary with 1031 thinners

Apply two full coats of Tikkurila PLS PU topcoat by airless spray, allowing at least 24 hours in between coats. De-nib in between coats using 180 grade silicon carbide paper pads. Thin if necessary with 1061 thinners.

Selected Colour: METALIC BRONZE TBC

