

# TECHNICAL DATA SHEET

supersedes previous issue dated 08/03/05

**AP 1221/XX**
**WATERBORNE HARMONISING GLAZE**

|                    |   |
|--------------------|---|
| Colours available: | 00 clear<br>07 golden yellow<br>08 red<br>09 orange<br>22 black<br>56 cherry<br>76 wenge<br>92 walnut<br>95 dark walnut |
| Area of use:       | Oak furniture, reproduction furniture   |
| Method of use:     | spray and wiping  |
| Thinning:          | 1:1 with water  |

### Technical characteristics

|                          |                                   |
|--------------------------|-----------------------------------|
| Solids content (%):      | 11 ÷ 22 depending on colour       |
| Specific gravity (kg/l): | 1.030 ÷ 1.100 depending on colour |

### General characteristics

|                      |   |
|----------------------|---|
| Light fastness:      | Excellent for interiors                               |
| Drying:              | 2 hours at room temperature                           |
| Overcoating:         | Waterborne, polyurethane and nitrocellulose topcoats. |
| Shelf-life (months): | 15  |

- Harmonising effect on uneven wood.
- Thanks to the high solids content, better pore filling and limited fibre raising are achieved than with conventional waterborne stains.
- If the colour to be reproduced is light, AP 1221/00 can be used and thinning shall be lower.
- No bleeding with waterborne coating systems.

### Special instructions

Stir well before use.

Before starting the coating system, make sure that the stain has had enough time to dry.

Always check the adhesion of the coating system used.

Do not store at temperatures below 10°C.