

# TECHNICAL DATA SHEET

supersedes previous issue dated 13/11/03

**WZ52\*\***
**MATT UREIC TOPCOAT**

Versions:	10, 25, 40 gloss		
Area of use:	General purpose, turned parts and furniture		
Method of use:	Conventional spray gun		
Mixing procedure:		by weight (kg)	by volume (lt)
	Part A	WZ52**	100
	Part B (catalyst)	WH1084	10
			100
			11

### Technical characteristics:

Solids content (%):	44 ± 2
Specific gravity (kg/l):	0.965 ± 0.030
Viscosity (DIN 4 at 20°C):	21" ± 1"

### Substrate preparation

With a polyurethane or ureic basecoat followed by sanding.

### General characteristics

Pot-life:	24 hours	
Recommended application weight (g/m <sup>2</sup> ):	100÷150	
Drying time (100 g/m <sup>2</sup> at 20°C):	Dust free	10'-15'
	Touch dry	60'-70'
	Stackable	6 hours
Forced drying (100 g/m <sup>2</sup> ):	Flash off	20'
	Hot air at 50°	40'
	Cooling	20'
Shelf-life:	If the product is properly stored, shelf-life is unlimited. After long periods of storage, always check homogeneity and stir well before use to eliminate any possible sediment.	

WZ52\*\* is a matt ureic clear topcoat. Its main characteristics are high wettability, fast drying and scratch resistance.

### Special instructions

The product must be applied at temperatures between 18° and 25°C.

Lower temperatures require longer drying times, whereas at higher temperatures it is necessary to thin with slow-drying thinners.

WZ52\*\* must be stored in warm places: do not use the product if it has been stored at temperatures below 15°C.

If necessary, warm the can in a water bath at 25-30°C for at least two hours.