

TYPICAL PAINT SPECIFICATION

INTERNAL PLASTER WALLS & CEILINGS – HYGIENE SYSTEM

PREPARATION

Thoroughly wash down overall using Tikkurila Cleaning Agent to remove all accumulated contamination, deposits, mould/algae, dirt, grease, salt, oil and all other contamination etc so as to present a clean surface.

Rinse well with clean water and allow to thoroughly dry.

Completely remove all loose, suspect poorly adhering, flaking or otherwise defective coatings back to a firm sound base.

Particular care needs to be taken to identify all poorly adhering coatings and thorough preparation to remove all defective coatings back to a sound base.

Dust off well.

Cut out all defective areas, mortar joints etc and make good with a good quality exterior grade filler and/or sand/cement mix. Allow to fully cure and dry out in depth.

Thoroughly abrade to provide a 'key' all exposed and glossy coatings.

It is important to ensure that the surfaces are perfectly clean sound and dry at the time of painting.

PAINTING

Patch Prime – All exposed/bare areas, plaster etc. Tikkurila Luja Universal Primer. Single pack water based.

Finish – Apply overall **Two coats** Tikkurila Luja Finishing Paint. Single pack water based high performance acrylate finish. DFT 50 Microns/coat.

NB: All products must be used in strict accordance with all relevant technical data sheets, attached letter and important notes.



TYPICAL PAINT SPECIFICATION

INTERNAL PLASTER WALLS/CEILINGS – TWO PACK WATER BASED FOR TOUGH DURABLE FINISH

PREPARATION

Treat all mould and algae deposits with Tikkurila Mould Removal fungicidal wash using strictly in accordance with the manufactures instructions. Allow to act before rinsing off wee with clean water.

Ensure all mould/algae residues are removed during the washing procedure.

Thoroughly wash down overall to remove all accumulated contamination dirt, grease, salt, oil and all other contamination etc so as to present a clean surface.

Rinse well with clean water and allow to thoroughly dry.

NB: The use of high pressure water jetting and steam cleaning equipment are recommended for cleaning these surfaces.

'Caked' on deposits may need to be manually scraped off or otherwise removed prior to the cleaning process.

Rinse well with clean water and allow to thoroughly dry.

Completely remove all loose, suspect poorly adhering, flaking or otherwise defective coatings back to a firm sound base.

Abrade overall or as required to remove all loose debris and to provide a 'key' if necessary.

Dust off well.

Cut out all defective areas, mortar joints etc and make good with a good quality exterior grade filler and/or sand/cement mix. Allow too fully cure and dry out in depth.

All steel bolts/fittings to be painted, as part of the wall decoration must be prepared in line with system 'A' and patch primed with Temabond ST 200/250 prior to painting.

It is important to ensure that the surfaces are perfectly clean sound and dry at the time of painting.

PAINTING – TWO PACK WATER BASED (FULL COLOUR RANGE)

1st Coat – Apply to all bare/porous areas. Tikkurila Akvacoat 100. Two pack water based epoxy intermediate/finish. Brush well into the surface until porosity is satisfied.

Finish – Apply overall 2 coats. Tikkurila Akvacoat 100. Two pack water based epoxy gloss finish. DFT 50 Microns/coat

All products must be used in strict accordance with all relevant technical data sheets and attached important notes.

PAINTING – SINGLE PACK WATER BASED HYGIENE COATING (FULL COLOUR RANGE)

1st Coat – Apply to all bare/porous areas. Tikkurila Akvacoat 100. Two pack water based epoxy intermediate/finish. Brush well into the surface until porosity is satisfied.

Finish – Apply overall 2 coats. Tikkurila Akvacoat 100. Two pack water based epoxy gloss finish. DFT 50 Microns/coat

All products must be used in strict accordance with all relevant technical data sheets and attached important notes.



TYPICAL PAINT SPECIFICATION

UNTREATED INTERNAL PLASTER/CONCRETE WALLS/CEILINGS

PREPARATION

Treat all mould and algae deposits with a Tikkurila Mould Removal fungicidal wash using strictly in accordance with the instructions. Allow too act before rinsing off with clean water.

Ensure all mould/algae residues are removed during the washing procedure.

Thoroughly wash down overall to remove all accumulated contamination dirt, grease, salt, oil and all other contamination etc so as to present a clean surface.

Rinse well with clean water and allow to thoroughly dry.

Abrade overall or as required to remove all loose debris and to provide a 'key' if necessary.

Dust off well.

Cut out all defective areas, etc and make good with a good quality exterior grade filler and/or sand/cement mix. Allow too fully cure and dry out in depth.

All steel bolts/fittings to be painted as part of the wall decoration must be prepared in line with system 'A' and patch primed with Temabond ST 200/WG 200 prior to painting.

It is important to ensure that the surfaces are perfectly clean sound and dry at the time of painting.

PAINTING

1st Coat – Apply overall. Tikkurila Akvacoat 100. Two pack water based epoxy gloss finish. DFT 50 Microns/coat. Thin up to 10 % with clean water and brush well into the surface until porosity is satisfied.

Finish – Apply overall 2 coats. Tikkurila Akvacoat 100. Two pack water based epoxy gloss finish. DFT 50 Microns/coat

All products must be used in strict accordance with all relevant technical data sheets and attached important notes.

