

TEMATHANE PLV & PLV(L)

DESCRIPTION

A two component, recoatable aliphatic polyurethane, gloss finish.

PRODUCT FEATURES AND RECOMMENDED USES

- ◆ Approved to Highways Agency Item 168 and Network Rail RT98 Item 7.3.1.
- ◆ Excellent chemical resistance.
- ◆ Excellent high gloss and gloss retention.
- ◆ Extremely tough, durable finish, combining good anti-abrasion properties with exceptional weathering characteristics.
- ◆ Easily cleaned finish.
- ◆ Withstands 150°C dry heat (discolouration may occur).
- ◆ EPA compliant as a finish.
- ◆ Low temperature curing – down to -5°C.

TECHNICAL DATA

Volume solids

53 ± 2% (ISO 3233).

Weight solids

66 ± 2%.

Specific gravity

1.10 – 1.30 mixed, depending on colour.

Product code

Paint	5 parts by volume	2892 (PLV) and 2905 (PLV(L))
Hardener	1 part by volume	4054 120
Composite		4800 (PLV) and 4885 (PLV(L))

Pot life

4 hours @ 23°C

Recommended film thicknesses and theoretical coverage

Recommended film thicknesses		Theoretical coverage
dry	wet	
30 µm	55 µm	17.6 m ² /l
60 µm	115 µm	8.8 m ² /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Drying time

DFT 40 µm		+5°C	+10°C	+23°C	+35°C
Dust free		3 h	2 h	1 h	45 min
Hard dry		9 h	6 h	3 h	2 h
Overcoating	Min	24 h	24 h	12 h	10 h
	Max	Indefinite* - see product notes			

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Finish

High gloss

Colours

BS4800, RAL, NCS, TVT colours, selected BS2660 and BS381C shades and metallic shades* (for Clear, see separate data sheet for Temathane PLV001).

TEMATHANE PLV & PLV(L)

APPLICATION DETAILS

Surface preparation	This is a finish coat which should be applied over appropriate Protega primers or undercoats. Consult Protega Coatings for advice. Surfaces should be clean, dry and free from grease, oil and general contamination.																			
Application conditions	Only apply in conditions of good ventilation which should be maintained during drying. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time of the paint coating, the surface should be dry, the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point.																			
Mixing	Mix only in the proportions stated, mixing each component individually then together using a mechanical agitator. Ensure complete homogeneity before use.																			
Application	<table><tr><th>Method</th><th>Airless spray</th><th>Automatic spray</th><th>Conventional spray</th><th>Brush</th><th>Roller</th></tr><tr><td>Output pressure</td><td>2200 – 2500 p.s.i.</td><td rowspan="2">No</td><td rowspan="2">Yes any suitable equipment</td><td rowspan="2">Yes</td><td rowspan="2">Yes</td></tr><tr><td>Tip size</td><td>13 – 18</td></tr></table> <p>Brush/Roller – product is suitable for brush and roller application, although due to fast curing properties, intricate structures should be avoiding with this method. Avoiding exceeding the maximum stated dry film thickness. The addition of 5 – 10% 1737 Thinners is recommended for best results when spraying, except with metallic shades, which should be applied without thinning.</p>						Method	Airless spray	Automatic spray	Conventional spray	Brush	Roller	Output pressure	2200 – 2500 p.s.i.	No	Yes any suitable equipment	Yes	Yes	Tip size	13 – 18
Method	Airless spray	Automatic spray	Conventional spray	Brush	Roller															
Output pressure	2200 – 2500 p.s.i.	No	Yes any suitable equipment	Yes	Yes															
Tip size	13 – 18																			
Thinner	1737 Thinner.																			
Cleaning of equipment	Remove remaining paint from equipment, flush thoroughly with 1737 Thinner until solvent appears uncontaminated.																			
FLASH POINT	22 - 32°C.																			
STORAGE	Store in dry, cool conditions and protect from frost.																			
HEALTH AND SAFETY	Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets. A health and safety data sheet is available on request from Protega Coatings Ltd.																			
PRODUCT NOTES	<p>*Metallic shades: can applied to 50 microns dft maximum for best appearance. Apply metallic shades over suitable undercoats from selected Protega epoxy or polyurethane materials. Viscosity and solids content of metallic shades are lower than standard colours. Please consult Protega Coatings for advice on specific metallic shades.</p> <p>Some shades contain lead colourants and these are labelled as Temathane PLV(L). High humidities and condensation will impair gloss. Caution - contains isocyanate. Ensure adequate ventilation and wear air fed hood when spraying. For PLV20, PLV50 or PLV90 products, with codes beginning 2901-, (formerly called <i>Temadur MS series</i>), please see separate “Temathane PLV20,50,90” 2901-line data sheet.</p>																			